

Arches CRS-2P - Ergon - Snowflake, AZ - BASF			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
91.6	544.8	497.8	13.8
90.5	545.5	511.0	10.1
88.8	547.7	506.9	11.8
88.4	555.6	515.5	11.4
91.6	552.9	523.4	8.5
AVG			11.1
STD			2.0
Range			5.3

Arches CRS-2P - Ergon - Snowflake, AZ - Paragon			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
65.9	533.8	474.5	16.9
66.1	559.7	497.6	16.7
66.1	552.7	494.3	16.0
65.3	562.2	499.8	16.7
65.4	541.2	483.7	16.1
AVG			16.5
STD			0.4
Range			0.9

Arches CRS-2P - Ergon - Snowflake, AZ - PRI			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
80.9	510.1	471.0	12.1
90.2	494.3	453.1	13.6
88.7	475.6	439.9	12.3
84.1	529.4	480.8	14.5
90.0	507.5	467.3	12.8
AVG			13.1
STD			1.0
Range			2.4

Death Valley CRS-2P - Western - Irwindale, CA - PRI			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
91.4	573.1	530.7	11.7
86.6	562.9	522.2	11.4
83.4	542.6	495.9	13.5
91.4	583.9	545.0	10.5
85.7	551.1	507.9	12.3
AVG			11.9
STD			1.1
Range			3.0

Death Valley CRS-2P - Western - Irwindale, CA - BASF			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
89.16	596.83	562.83	8.9
87.42	605.84	572.05	8.7
91.85	615.84	582.52	8.5
91.63	591.38	547.52	11.7
89.22	604.58	562.05	11.0
AVG			9.7
STD			1.5
Range			3.2

Death Valley CRS-2P - Western - Irwindale, CA -Paragon			
Felt Wt (g)	Initial Wt (g)	Final Wt (g)	Mass Loss (%) ((A-B)/(A-C))*100*1.33
67.6	592.1	487.9	26.4
67.2	596.6	493.6	25.9
66.8	602.4	496.8	26.2
68.1	585.2	486.5	25.4
66.9	594.4	490.3	26.2
AVG			26.0
STD			0.4
Range			1.0
Dinosaur National Monument - Pass - PRI			

Insufficient curing at two hours - all chips lost