
Standard Specification for

**Materials for Emulsified Asphalt
Scrub Seal**

AASHTO Designation: MP xxx-18¹

Technical Section: 5b, Bridge and Pavement Preservation

Release: Group 1 (April)

AASHTO

**American Association of State Highway and Transportation Officials
444 North Capitol Street N.W., Suite 249
Washington, D.C. 20001**

Materials for Emulsified Asphalt Scrub Seal

AASHTO Designation: MP xxx-18¹



Technical Section: 5b, Bridge and
Pavement Preservation

Release: Group 1 (April)

1. SCOPE

- 1.1. A scrub seal is the application of emulsified asphalt with a scrub broom followed immediately by an application of a single layer of cover aggregate. The treatment can be applied as a wearing surface or as an interlayer.
- 1.2. This standard specifies quality requirements for aggregate and emulsified asphalt for scrub seals.
-

2. REFERENCED STANDARDS

2.1. *AASHTO Standards:*

- M 140, Emulsified Asphalt
- M 208, Cationic Emulsified Asphalt
- M 316, Polymer-Modified Emulsified Asphalt
- R 66, Sampling Asphalt Materials
- R 78, Recovering Residue from Emulsified Asphalt Using Low-Temperature Evaporative Techniques
- T 11, Materials Finer Than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing
- T 27, Sieve Analysis of Fine and Coarse Aggregates
- T 49, Penetration of Bituminous Materials
- T 96, Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine
- T 111, Mineral Matter or Ash in Asphalt Materials
- T 179, Effect of Heat and Air on Asphalt Materials (Thin Film Oven Test)
- T 201, Kinematic Viscosity of Asphalts (Bitumens)
- T 202, Viscosity of Asphalts by Vacuum Capillary Viscometer
- T 240, Effect of Heat and Air on a Moving Film of Asphalt Binder (Rolling Thin-Film Oven Test)
- T 301, Elastic Recovery Test of Asphalt Materials by Means of a Ductilometer
- T 335, Determining the Percentage of Fracture in Coarse Aggregate
- T 350, Multiple Stress Creep Recovery (MSCR) Test of Asphalt Binder Using a Dynamic Shear Rheometer

2.2. *ASTM Standards:*

- D471, Standard Test Method for Rubber Property—Effect of Liquids

- D4124, Standard Test Method for Separation of Asphalt into Four Fractions
- D7226, Standard Test Method for Determining the Viscosity of Emulsified Asphalts Using a Rotational Paddle Viscometer
- D7403, Standard Test Method for Determination of Residue of Emulsified Asphalt by Low Temperature Vacuum Distillation
- D7944, Standard Practice for Recovery of Emulsified Asphalt Residue Using a Vacuum Oven

2.3. *Federal Lands Highway (FLH) Standard:*

- FLH T 508, Flakiness Index Value

3. TERMINOLOGY

3.1. *Definition:*

- 3.1.1. *polymer modified rejuvenating emulsion (PMRE)*—Medium setting emulsified asphalt for scrub seal application that meets the requirements of Table 1 and includes components that meet the requirements of Tables 2 and 3.

4. SIGNIFICANCE AND USE

- 4.1. This standard may be used to select and evaluate materials for the construction of emulsified asphalt scrub seals.

5. POLYMER MODIFIED REJUVENATING EMULSION (PMRE) REQUIREMENTS

- 5.1. Sample, store, and test within the time frame specified in section 3.1 of M 316. Refer to Section 3.1 for definition of sample condition that is indicative of a compromised sample that must be discarded.
- 5.2. Emulsified asphalt (PMRE) for scrub seal shall meet the requirements of medium setting type cationic emulsified asphalt, rejuvenating agent, and modifier in Tables 1 through 3. Table 1 includes specification requirements for two viscosity test methods. For certification and acceptance testing, either one or both can be used.

Table 1—Requirements for Scrub Seal Emulsified Asphalt (PMRE)

Grade	PMRE ^a	
	Min	Max
Tests on Emulsified Asphalt		
Viscosity, Saybolt Furol, 50°C (122°F) ^b , s	50	400
Viscosity, Rotational Paddle Viscometer, 50°C (120°F), cPs	110	880
Storage stability test, 24 h, % ^b		1.0
Demulsibility, 35 mL, 0.8% Sodium Dioctyl sulfosuccinate, %	Report Only	
Sieve test, %:		0.10
Particle charge	Positive	
Distillation ^c :		
Oil distillate, by volume of emulsified asphalt, %		1
Residue, %	65	
Tests on residue from distillation ^d :		
Penetration, 4°C (39°F), 200 g, 60 s, 0.1 mm	40	
MSCR Percent Recovery at 3.2 kPa, 10°C (50°F), %	55	—
Ash Content, %		1
Viscosity, 60°C (140°F), Pa·S	—	5000

^a Samples of emulsified asphalt will be taken in accordance with R 66, M 140, M 208, and M 316. Samples must be stored at a temperature of not less than 4°C until tested.

^b This test requirement and associated specification limits are waived if successful applications of the material are achieved in the field.

^c Distill to 175°C (347°F).

^d Residue preparation for testing may use the alternate methods, R 78, ASTM D7403, or ASTM D7944, so as not to negatively affect the properties of any polymer modifiers contained therein.

5.3. Alternate recovery methods as defined in Table 1, Note d may be used to prepare the emulsified asphalt residue for testing in accordance with Table 1, if approved by the owner.

5.4. Note 1. Properties of the residue recovered using alternate methods may differ from those obtained after distillation. The same method to prepare the residue must be used when comparing test results from the residue.

Table 2—Tests on Rejuvenating Agent

	Method	Min	Max
Tests on Rejuvenating Agent			
Viscosity, 60°C (140°F), CST	T 201	50	300
Flash Point, °C (°F)	T 48	193 (380)	
Saturates, %	ASTM D4124		30
Tests on TFO or RTFO Residue			
Mass Change, %	T 179 or T 240		6.5
Viscosity Ratio	T 179 or T 240		3

Table 3—Tests on Modifier

	Method	Min	Max
Tests on Modifier			
Mass Change, %	ASTM D471 (modified)		60%

5.5. *Modify ASTM D471 as follows:*

5.5.1. Place 0.8 g of modifier into an 18-mm diameter DSR mold.

5.5.2. If necessary, dry at ambient lab conditions for 72 hr.

- 5.5.3. Remove the modifier from the mold and place the sample into a forced draft oven on release paper for 48 hr at 40°C.
- 5.5.4. After 48 hr, cool and weigh the sample to the nearest 0.0001 g. Record the weight.
- 5.5.5. Pour 30 g of rejuvenating agent in a 90-mL metal container.
- 5.5.6. Place modifier sample in the container and add another 30 g of rejuvenating agent. Ensure the latex or polymer sample is completely covered; add more rejuvenating agent if necessary.
- 5.5.7. Cover the container with a metal lid and place it into a 40°C oven for 48 hr.
- 5.5.8. Remove the sample from the container. Use a paper towel to blot the surface of the sample to remove excess rejuvenator. Allow sample to cool to room temperature and weigh to the nearest 0.0001 g.
- 5.5.9. Calculate the mass change, expressed in Equation 1. Mass change will be positive.

$$\text{Mass Change (\%)} = \frac{M_2 - M_1}{M_1} \quad (1)$$

where:

M_1 = Mass of modifier sample before being conditioned in the rejuvenating agent (g); and

M_2 = Mass of modifier sample after conditioning in the rejuvenating agent (g).

6. AGGREGATE REQUIREMENTS

- 6.1. Scrub seal cover aggregate shall be durable and free from deleterious materials. Gradations requirements are specified in Table 4. All percentages are by weight. The aggregate type will be determined by the owner agency. Aggregate retained on the 4.75-mm (No. 4) screen shall be crushed by mechanical means meeting the requirements shown in Table 5.

Table 4—Scrub Seal Aggregate Gradation Limits

Nominal Sieve Size	Passing, %		
	Type I	Type II	Type III
12.5 mm (1/2 in.)	100	100	100
9.5 mm (3/8 in.)	90–100	90–100	100
7.9 mm (5/16 in.)	—	—	90–100
4.75 mm (No. 4)	5–20	10–30	10–80
2.36 mm (No. 8)	0–5	0–10	5–30
1.18 mm (No. 16)	0–5	0–5	0–15
0.075 mm (No. 200)	0–3	0–3	0–5

Table 5—Fracture and Quality Requirements

Property	Scrub Seal Application	
	Interlayer	Surface Treatment
Fracture, 1 Face, % min T 335	70	85
Fracture, 2 Faces, % min T 335	60	80
Los Angeles Abrasion, max. % loss, T 96	37	35
Flakiness Index Value, max. % , FLH T 508	35	30

7. KEYWORDS

7.1. Polymer modified emulsion; rejuvenator; scrub seal.

¹ This provisional standard was first published in 20yy.

WORKING DRAFT